



K82000 Series Clear Polyurethane - Aliphatic

These premium quality extruded aliphatic polyurethane films have been specially developed for use in the automotive and other industries which require a self adhesive material to reduce corrosion, stone chipping and scratching. Polyurethane may also be used for anti-squeak applications. The films are clear and have a specially developed Hi Tack aggressive adhesive system, which makes them suitable for use under or over painted surfaces.

The materials have performed successfully when printed by rotogravure screen and digital methods using solvent based inks, as well as thermal transfer imaging. However it is advisable to test the process prior to any production run.

These films are available as:

K82300	300 micron with 60gsm of adhesive
K82250	250 micron with 60gsm of adhesive
K82200	200 micron with 60gsm of adhesive
K82150	150 micron with 50gsm of adhesive
K82137	137 micron with 50gsm of adhesive
K82125	125 micron with 40gsm of adhesive
K82100	100 micron with 40gsm of adhesive
K82075	75 micron with 40gsm of adhesive

All materials are available with a paper or antistatic polyester liner, with or without PE or PET protective film and are often subject to minimum order quantities. Other thicknesses are available please contact sales@kpmf.com for further information.

CHARACTERISTIC

Film Thickness
 Adhesive Thickness
 Adhesive Type
 Release Liner

Storage

Tensile (K82200)
 Elongation (K82200)
 Shore Hardness A
 Static Shear
 Adhesion 20 Mins/180° 23°C
 Adhesion 24 Hrs/180° 23°C
 Dimensional Stability
 (150 x 150mm/48 hours) 70°C
 Gravel Resistance (K82200)

Abrasion Resistance
 Fuel Resistance
 Environmental Resistance

Weathering

TEST METHOD

ISO 4591:1992
 ISO 4591:1992

ISO 527:1996
 ISO 527:1996

FINAT FTM8/Stainless Steel
 FINAT FTM1/Stainless Steel
 FINAT FTM1/Stainless Steel
 FINAT FTM14/Aluminium

SAE J400 2.4L of gravel
 1. 48 Hrs at 23°C
 2. 48 Hrs at 23°C & 4 Hrs at -30°C
 3. 4 Hrs at -30°C two cycles GM 950SP-F
 1000 Cycles, 500g load, CS-17 Wheel

Vertical Exposure/Mid Europe

TYPICAL VALUE K82200

See above
 See above
 Hi Tack Self Cross Linking Acrylic
 140gsm Stayflat Kraft/75µ antistatic matt backed polyester
 Two years, out of direct sunlight at 73° F and 50% humidity. Where the film is supplied without either protective film attached, the shelf life under the same conditions above is reduced to three months.
 30 N/mm²
 250%
 90-95 units
 2 hours
 430 N/m Minimum
 710 N/m Minimum
 1.0mm

Shall not exceed approved test sample.
 Shall not exceed approved test sample.
 Shall not exceed approved test sample.
 No wear through to substrate.
 No blistering, visible shrinkage or edge lifting
 No blistering visible shrinkage or edge lifting.
 No discoloration (DE measured on white standard in CMC 2) greater than: -
 1. 2500 KJ WOM 1.5 ΔE Maximum
 2. 168 Hrs @ 70°C 2.5 ΔE Maximum
 3. 168 Hrs @ 120°C 18.0 ΔE Maximum
 4. 168 Hrs Humidity 2.0 ΔE Maximum
 6-8 Years

KPMF films should not be applied to unsound surfaces or to surfaces which may subsequently crack, peel, outgas or are of low surface energy. It is recommended that any application surface should have an energy level in excess of 40 dyne/cm. (Polyolefins should be in excess of 45 dyne/cm). The above data shows typical properties and should not be taken as a guarantee for performance. Purchasers should determine the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Durability is based on middle European exposure conditions. Actual performance will depend on substrate preparation, exposure conditions and application of marking.

IMPORTANT

Kay Premium Marking Films are produced under stringent manufacturing conditions. The information and typical values shown are based upon research believed to be reliable and are provided without guarantee and do not constitute a warranty. The values are not for use in specifications. Ink and paint systems can affect the performance of film and also the adhesive properties, as can application techniques. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use.

WARRANTY

Kay Premium Marking Films are produced under careful quality control and are warranted to be fit for the purpose and free from defect in material and workmanship. Any material shown to be defective to our satisfaction at the point of sale shall be replaced free of charge. Kay Premium Marking Films Limited liability to the purchaser shall in no circumstances exceed the cost of the amount of the defective material supplied.