



**K71400 Series Visual Effects Matt Cast Vinyl Over-Laminating Films**

A luxury and innovative over-lamine that transforms any application with the creation of a sparkling starlight appearance. These high quality 60 micron cast matt over-laminating films have been specially developed for use in the digital imaging industry to permanently enhance and protect the printed media. They offer a premium solution to over-laminating applications by using a solvent based acrylic adhesive system.

The film is available as:-

K71401	Pink Starlight Matt Overlamine
K71402	Gold Starlight Matt Overlamine
K71403	Pacific Blue Starlight Matt Overlamine

CHARACTERISTIC	TEST METHOD	TYPICAL VALUE
Film Thickness	ISO 4591:1992	60 micron
Adhesive Thickness	ISO 4591:1992	25 micron
Adhesive Type		Clear Permanent Acrylic
Release Liner		Double Sided PE Liner
Storage		Two years, out of direct sunlight at 23°C and 50% humidity
Tensile	ISO 527:1996	>13.5 N/mm <sup>2</sup>
Elongation	ISO 527:1996	>50%
Adhesion 20 Mins/180°	FINAT FTM1/Painted Plate	450 N/Metre
Adhesion 24 Hrs/180°	FINAT FTM1/Painted Plate	530 N/Metre
Static Shear (25 x 25mm)	FINAT FTM8/Stainless Steel	>16 hours
Dimensional Stability (150 x 150mm/48 hours/70°C)	FTM14/Aluminium	<0.4mm
Gloss 60°	ASTM 523-89	>85%
Flammability		Self Extinguishing
Artificial Weathering	Atlas Xenon arc	>1000 hours
Weathering	Vertical Exposure/Mid Europe	Ongoing
Application Temperature	Clean, dry surface	+8°C to 25°C
Service Temperature		-40°C to +105°C
<b>Resistance to various liquids after application and conditioned for 24 hours at 23°C. Results examined 1 hour after test.</b>		
Humidity	24 hours at 38°C and 100%	No Effect
Water (Distilled)	24 hours at 32°C	No Effect
Sea Water	1 year Mid Tide (BS 5609:1986)	No Effect
Reference Fuel	1 hour at 23°C	Very Slight Film Softening
Diesel Fuel	1 hour at 23°C	No Effect
SAE Motor Oil	24 hours at 23°C	No Effect
Antifreeze/Water (1:1)	24 hours at 23°C	No Effect
Detergent Solution	8 hours at 65°C	No Effect
Hydraulic Oil	24 hours at 23°C	No Effect
Battery Acid	24 hours at 23°C	No Effect

Although we have good control of the colour production at KPMF, it is advisable to avoid using different batches of material for the same end application

KPMF films should not be applied to unsound surfaces or to surfaces which may subsequently crack, peel, outgas or are of low surface energy. It is recommended that any application surface should have an energy level in excess of 40 dyne/cm. (Polyolefins should be in excess of 45 dyne/cm). The above data shows typical properties and should not be taken as a guarantee for performance. Purchasers should determine the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Durability is based on middle European exposure conditions. Actual performance will depend on substrate preparation, exposure conditions and application of marking.

**IMPORTANT**

Kay Premium Marking Films are produced under stringent manufacturing conditions. The information and typical values shown are based upon research believed to be reliable and are provided without guarantee and do not constitute a warranty. The values are not for use in specifications. Ink and paint systems can affect the performance of film and also the adhesive properties, as can application techniques. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use.

**WARRANTY**

Kay Premium Marking Films are produced under careful quality control and are warranted to be fit for the purpose and free from defect in material and workmanship. Any material shown to be defective to our satisfaction at the point of sale shall be replaced free of charge. Kay Premium Marking Films Limited liability to the purchaser shall in no circumstances exceed the cost of the amount of the defective material supplied.